

219
Gloss Clear
WINDOWS

Concept[®]
MEDIA SOLUTIONS

NEW

219 6.0 MIL GLOSS CLEAR
S E M I - R I G I D V I N Y L




THE CLEAR CHOICE FOR WINDOW GRAPHICS!

THICK, RIGID and EASY TO APPLY, perfect for WINDOW application

New **CONCEPT**[®] 219 is a premium LOW-TACK REMOVABLE 6.0 mil "Gloss Clear" semi-rigid vinyl that was designed for EASY APPLICATION TO WINDOWS. This film can be printed with solvent, eco-solvent, UV curable and latex inks.

Roll Size - 54" x 100 ft. - \$251.00 (.56 sq. ft.)

Concept[®]
MEDIA SOLUTIONS



General[®]
FORMULATIONS

MANUFACTURERS OF
PRESSURE
SENSITIVE FILMS
MADE IN THE U.S.A.

www.generalformulations.com

Graphic Commerce Ltd. Mississauga, On (905)624-3124 toll free 1-800-543-2796

Product Bulletin

Concept[®] 219 SEMI RIGID GLOSS CLEAR PVC REMOVABLE ADHESIVE

Concept[®] 219 is a 6.0 mil premium clear gloss semi rigid calendared vinyl film coated with 200-4982 removable acrylic pressure sensitive adhesive laminated to a 90# tight release digital liner designed for roll processing . This film is designed to accept a variety of solvent-based, UV curable and latex inks common to wide format digital printing systems.

Applications

Concept[®] 219 is a high performance removable decal film designed for ease of application of temporary interior or exterior signage, decals, nameplates, die-cut letters and point-of-purchase displays. Concept[®] 219 is the ideal media for temporary store front applications requiring bond to windows. This media may also be used on smooth surfaces such as metals, painted metals and certain high energy plastics.

Thickness

Film	6.0 mils.
Adhesive	.8 to 1.0 mils.
Liner	6.7 mils.
(Thickness variance +/- 10%)	

Gloss Initial @ 60°

75 minimum

Dimensional Stability

Good.

Temperature Ranges

Minimum application temperature	+40 °F.
Service temperature	-40 °F to +180 °F.

Expected Exterior Exposure

Interior
Exterior

Removable up to twelve (12) months under normal conditions.
Removable up to six (6) months under normal conditions.

Adhesion

To glass	4 to 16 oz. /in.
To standard test panels	4 to 16 oz. /in.

Tested according to PSTC-101 Method A with 24-hour dwell at 70 °F and 50% relative humidity. Typical values. Individual values may vary. Test thoroughly before production.

Water Resistance

Good. Test if immersed.

Humidity Resistance

Good.

Solvent Resistance

Good

Storage Stability

6 months shelf life when stored at 70 °F and 50% relative humidity.

Product Codes

219-54 (54" X 100' roll)

Recommendations

Completely evaporate inkjet solvents before application. Failure to do so may facilitate solvent penetration resulting in vinyl degradation.



**Manufacturer of Pressure Sensitive Films,
Traffic Graffice Floor Advertising Films,
Custom Coatings and Printing Inks.**

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537
Web Site: www.generalformulations.com • e-mail: gfiinfo@generalformulations.com

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.