



TURNING BLAND TO GRAND

Technical Data Sheet

SolvoPrint™ Easy Dot Matte

Carrier			
Film Type	Monomeric Plasticized Opaque White Matte PVC		
Thickness (mil)	4.0		
Gloss (Dr. Lange reflectometer, 85° measuring angle)	>10		
Breaking Force (N/15mm)	Lengthwise: >50	Crosswise: >40	
Elongation at Tear (%)	Lengthwise: >150	Crosswise: >200	
Tear Resistance (N/mm ²)	Lengthwise: >30	Crosswise: >20	
Adhesive			
Adhesive Type	Polyacrylate dispersion, dots		
pH-value	Approx. 7		
Adhesive Strength (N/25 mm)	10 min: > 1.0	24h: > 1.5	AFERA 4001
Release Liner			
Type	Siliconized white PE paper, neutral		
Thickness (mil)	6.3		
Other			
Handling/Storage Conditions	18 to 25 C / 60 to 80 F; 40 to 65% relative humidity		
Temperature Stability	-30 to 50 C / -22 to 122 C		

Advantages / Special Features

- Outdoor durability (unprinted) 1 year – depending on application area and purpose
- Dot patterned adhesive allows for bubble and wrinkle free application
- No special tools required for installation or removal
- White matte finish

Process & Handling

- A sufficient drying time, min. 24 hours, is required

Recommended Inks	
Solvent	◆
Eco Solvent	◆
UV	◆
Latex	◆

ICC Profiles

For Technical Support with any of our inkjet print materials, please call Seal Media Support at 800-257-7325, ext. 8945.



April 2013

Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. The purchaser should test material to determine if it is suitable for their own specific purpose.